



AMERICAN ACCENTS® 2X ULTRA COVER™ PRIMER SPRAYS

DESCRIPTION AND USES

American Accents® 2X Ultra Cover™ contains technology that provides twice the coverage on wood, metal, most plastic, wicker and more when compared to other matching colors of Rust-Oleum general purpose paints: Painter's Touch, SPRAY N GO, Quick Color and Touch 'n tone. It covers surfaces with less spray passes, allowing projects to be completed faster and easier. Any angle spray feature allows you to spray in any direction, even upside down. Fast Drying.

TIP: Some plastics made of polyethylene such as plastic storage containers are manufactured in a way that may hinder maximum paint adhesion. Test paint in a hidden area first.

PRODUCTS

SKU	DESCRIPTION (Aerosol)
327911	Black Primer
327912	Gray Primer
327913	Red Primer
327914	White Primer

PRODUCT APPLICATION

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 65% to ensure proper drying. Do not use on objects that may exceed 200°F (93°C) surface temperature. Do not apply to galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

SURFACE PREPARATION

ALL SURFACES: Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile.

STEEL: Scrape and wire brush or power tool clean to remove loose rust, scale and deteriorated previous coatings.

PREVIOUSLY COATED: Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile. The American Accents 2X Ultra Cover Primers are compatible with most coatings, but a test patch is suggested.

PRODUCT APPLICATION (cont.)

WARNING! If you scrape, sand or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE; ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply multiple light coats versus one heavy coat. Wet sand on metal and dry sand on wood too achieve the smoothest, most uniform base for the topcoat. Use #400 grit wet or dry sandpaper. For best results, let dry at least 30 minutes before wet sanding. Do not use near open flame.

NOTE: On plastic maximum paint adhesion and durability is achieved in 5-7 days.

DRY & RECOAT

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 20 minutes, to handle in 1 hour, and is fully dry in 24 hours. Apply a second coat or American Accents 2X Ultra Cover topcoat within 1 hour or after 48 hours.

CLEAN-UP

When finished spraying, wipe off tip before storing. Clean up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If valve clogs, twist and pull off spray tip and rinse it in a solvent such as mineral spirits. Do not stick pin or other object into the stem.

TECHNICAL DATA**AAC-20**

AMERICAN ACCENTS®

2X ULTRA COVER™ PRIMER SPRAYS

PHYSICAL PROPERTIES

		2X ULTRA COVER PRIMER SPRAYS
Resin Type		Acrylic Modified Alkyd
Pigment Type		Varies with Color
Solvents		Acetone, n-Butyl Acetate, Naptha, Xylene
MIR		0.70 Max
Fill Weight		12 oz.
Recommended Dry Film Thickness (DFT) per Coat		1.5 – 2.5 mils (37.5 – 62.5µ)
Practical Coverage at Recommended DFT (assume 15% material loss)		10-12 sq.ft./can (0.9-1.1 m ² /can)
Dry Times at 70°F (21°C) and 50% Relative Humidity	Touch	20 minutes
	Handle	1 hour
	Recoat	Within 1 hour or after 48 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation
11 Hawthorn Parkway
Vernon Hills, Illinois 60061

Phone: 877-385-8155
www.rustoleum.com

Form: ARJ-1583
Rev.: 110118